

Grade: 316L

Typical Analysis

Elements	<u>C</u>	<u>Si</u>	<u>Mn</u>	<u>Cr</u>	<u>Ni</u>	<u>Mo</u>	<u>N</u>	<u>V</u>	<u>W</u>	<u>Co</u>	<u>P</u>	<u>S</u>
	0.03 max	0.75 max	2.00 max	17.00	12.00	2.50	0.10 max	-	-	-	0.045 max	0.03 max

We acknowledge that the above figures are correct as contained in the records of the manufacturer.

QUALITY ASSURANCE

This is a typical analysis, the information contained herein encompasses the material delivered. If this document does not meet your needs, please contact Sales for further support.

USA

2505 Millennium Drive
Elgin, Illinois, 60124
Tel: 1 (877) 374 5763

Canada

2595 Meadowvale Blvd.
Mississauga, Ontario, L5N 7Y3
Tel: 1 (866) 807-0383