

## Grade: ASTM A36

### Typical Analysis

Elements	<u>C</u>	<u>Si</u>	<u>Mn</u>	<u>Cr</u>	<u>Ni</u>	<u>Mo</u>	<u>V</u>	<u>W</u>	<u>Co</u>	<u>P</u>	<u>S</u>
<b>Min</b>	-	-	-	-	-	-	-	-	-	-	-
<b>Max</b>	0.29	0.40	1.35	-	-	-	-	-	-	0.04	0.05

We acknowledge that the above figures are correct as contained in the records of the manufacturer.

#### QUALITY ASSURANCE

This is a typical analysis, the information contained herein encompasses the material delivered. If this document does not meet your needs, please contact Sales for further support.

#### USA

2505 Millennium Drive  
Elgin, Illinois, 60124  
Tel: 1 (877) 374 5763

#### Canada

2595 Meadowvale Blvd.  
Mississauga, Ontario, L5N 7Y3  
Tel: 1 (866) 807-0383