

## Grade: ASTM A514

### Typical Analysis

Elements	C	Si	Mn	Cr	Ni	Mo	V	Ni	Ti	Z	Cu	B	Nb	P	S
<b>Min</b>	0.10	0.15	0.40	-	-	0.10	-	-	-	-	-	-	-	-	-
<b>Max</b>	0.21	0.80	1.50	2.00	1.50	0.60	0.08	1.50	0.10	0.15	0.50	0.005	0.06	0.030	0.030

We acknowledge that the above figures are correct as contained in the records of the manufacturer.

#### QUALITY ASSURANCE

This is a typical analysis, the information contained herein encompasses the material delivered. If this document does not meet your needs, please contact Sales for further support.

#### USA

2505 Millennium Drive  
Elgin, Illinois, 60124  
Tel: 1 (877) 374 5763

#### Canada

2595 Meadowvale Blvd.  
Mississauga, Ontario, L5N 7Y3  
Tel: 1 (866) 807-0383